

step roof PVC

Produktdatenblatt Nr. 9224 - R - 05

Issue: June 2021

KRAITEC® step roof PVC is a protective mat made of rubber granules with PVC cladding on the bottom that is used on flat roofs with PVC foil covering as a walkway for maintenance, inspection and installation. **KRAITEC® step roof PVC** is also used as a protective layer under roof structures (e.g. solar installations, antennas, ply separation, etc.). **KRAITEC® step roof PVC** features PVC non-woven cladding on the bottom as an integrated separating layer in case of incompatibility with the roofing felt. The PVC cladding enables permanent bonding to the PVC roofing felt by means of hot-air welding to prevent lifting or slipping.

Material

Material:

Polyurethane-bonded recycled rubbergranulate with PVC cladding on the bottom.(typical rubber smell possible)

Product design

Colour:	red, green, grey or black (slight material-related colour variations possible)
Surface:	smooth with open pores, bevelled edges
Lower side:	PVC-cladding with drainage channels

Dimensions / Tolerances / Weight

Length x Width x Thickness:	500 mm x 500 mm, 30 mm
Tolerances:	length and width ± 1.5 %, thickness ± 2 mm
Weight slab:	approx. 5.3kg
Area weight:	approx. 21.1 kg / m ²

The product data sheet is not subject to any change service! All information is without guarantee.

Latest version of this document available on www.kraiburg-relastec.com/kraitec

page 1 of 5

step roof PVC

Produktdatenblatt Nr. 9224 - R - 05

Issue: June 2021

The product data sheet is not subject to any change service! All information is without guarantee.

Latest version of this document available on www.kraiburg-relastec.com/kraitec

page 2 of 5

Product Testing

Fire resistance:	Efl (B2) (EN 13501-1) Broof (t1) (DIN EN 13501-5)
Chemical resistance:	conditionally resistant to acids and bases
Environmental resistance:	rot-proof and water-resistant
Compression under traffic load:	10 % at approx. 18 t/m ² 20 % at approx. 38 t/m ² (Test method based on DIN EN ISO 3386-2)
Water drainage capacity:	at hydraulic gradient $i = 0,015$: 0,037 l/(m·s) in direction of drainage channels 0,022 l/(m·s) in transverse direction (Test method based on DIN EN ISO 12958) at hydraulic gradient $i = 0,05$: 0,097 l/(m·s) in direction of drainage channels 0,070 l/(m·s) in transverse direction (Test method based on DIN EN ISO 12958)
Frost-resistant:	yes
Salt water resistance:	fully resistant (DIN EN ISO 175 and DIN EN ISO 3386-2)
UV-Resistance:	fully resistant (DIN EN 1297 and DIN EN ISO 3386-2) (colour variations are possible due to environmental influences)
Anti-slip properties:	R10 (for work rooms and work areas with danger of slipping according to DIN 51130: 2014-02)
Chlorine resistance:	fully resistant (DIN EN ISO 175 and DIN EN ISO 3386-2)
Plasticizer migration:	is avoided by PVC cladding
Displacement space:	Class V4 (to DIN 51130:2015-02)
Wind suction loads:	Depending on the wind suction security of the PVC sealing Membrane, KRAITEC® step roof PVC can be used in all wind load zones when hot-air welded in an appropriate professional manner.

The product data sheet is not subject to any change service! All information is without guarantee.

Latest version of this document available on www.kraiburg-relastec.com/kraitec

page 3 of 5

step roof PVC

Produktdatenblatt Nr. 9224 - R - 05

Issue: June 2021

Impact sound insulation:

The readings have been raised with the full specified layer structure in a laboratory measurement. (In accordance with ISO 10140)

Warm roof		
PIR-insulation 140mm	Waterproofing: Bituminous roofing membranes	Waterproofing: PVC roofing membranes
Impact sound insulation improvement	$\Delta L_w = 27 \text{ dB}$	$\Delta L_w = 32 \text{ dB}$
Layer structure (top to bottom)	<ul style="list-style-type: none"> - KRAITEC® step - 2nd waterproofing layer: PYE PV 200 S 5, slate-coated - 1st waterproofing layer: G 200 S 4, talcum-coated - Insulation: PIR FA WLS 024 (140 mm) - Bitumen vapour barrier: V 60 S 4 + Al 	<ul style="list-style-type: none"> - KRAITEC® step plus - Waterproofing: PVC 1,5mm - Insulation: PIR FA WLS 024 (140 mm) - Bitumen vapour barrier: V 60 S 4 + Al AL

Installation

Installation is to be carried out in accordance with the **KRAITEC® step roof PVC** installation instructions.

The product data sheet is not subject to any change service! All information is without guarantee.

Latest version of this document available on www.kraiburg-relastec.com/kraitec

page 4 of 5

Other

- Other: Plastic connector pins included, pre-drilled holes on two sides of the slab (pre-drilled holes on four sides of the slab on request)
- Disclaimer: We want to use this information to advise you to the best of our knowledge and belief on the basis of our tests and experience. However, KRAIBURG Relastec GmbH & Co. KG cannot provide a guarantee for KRAITEC® products for the laying results in individual cases due to the wide range of application possibilities and the storage, laying and construction site conditions, which are outside our influence. You should carry out your own tests. Our technical service would be pleased to assist you.