

## golf slab EPDM

**Product data sheet no. 9152 - R-05**

Issue: February 2022

**SPORTEC® golf slab EPDM** is the ideal flooring for walkways, terraces and teeing areas on golf courses. It offers a pleasant waling feeling and protects the golf club by its springy effect. The integrated connector pin system allows cost-effective and easy installation. The installation in T-connection guarantees a very good dimensional stability. Environmentally friendly production and recycling. (KRAIBURG Relastec GmbH & Co.KG double recycling guarantee).

## Material

Material:

Recycling tyre rubber granules bonded with polyurethane elastomer, surface made of EPDM granules bonded with polyurethane elastomer.

## Product design

Colour(s):                      substructure: red  
   surface: according to EPDM colour pattern  
   (other colours on request)  
   (small colour differences can occur due to raw  
   material)

Colour(s):



beige RAL 1014, yellow RAL 1002, blue RAL 5015, leuchtblau RAL 5012, leuchtgrün RAL 6017

Surface: open-pored smooth  
Lower side: dimpled

The product data sheet is not subject to any change service! All information is without guarantee.

Latest version of this document available on [www.kraiburg-relastec.com/sportec](http://www.kraiburg-relastec.com/sportec)

page 1 of 3

**golf slab EPDM****Product data sheet no. 9152 - R-05**

Issue: February 2022

**Dimensions / Tolerances / Weight**

|                 |                                |
|-----------------|--------------------------------|
| Thickness(es):  | 30 mm ( $\pm 2$ mm)            |
| Length x width: | 500 x 500mm ( $\pm 0.8$ %)     |
| Area weight:    | approx. 22.4 kg/m <sup>2</sup> |

**Product Testing**

|                          |   |
|--------------------------|---|
| Fire resistance:         | Cfl-s1 (B1) (EN 13501-1)  |
| Tensile strength:        | 1.16 N/mm <sup>2</sup> (EN ISO 1798)  |
| Elongation at break:     | 78% surface (EN ISO 1798)<br>58% substructure (EN ISO 1798)   |
| Hardness:                | 60 $\pm$ 5 Shore A (DIN 53505)  |
| Resistance:              | conditionally resistant to acids and bases (internal tested)<br>Salt water resistance: resistant to DIN EN ISO 175, DIN EN ISO 3386-2 |
| Temperature range:       | -30° C to 80° C (internal tested)   |
| Wear behaviour:          | rV = 5.9 (DIN V 18035-6)  |
| Coefficient of friction: | wet: 0.53 $\mu$ (DIN 18032-2:2001-04)<br>dry: 0.62 $\mu$ (DIN 18032-2:2001-04)  |
| VOC emission rating:     |   |



The product data sheet is not subject to any change service! All information is without guarantee.

Latest version of this document available on [www.kraiburg-relastec.com/sportec](http://www.kraiburg-relastec.com/sportec)

page 2 of 3

## golf slab EPDM

Product data sheet no. 9152 - R-05

Issue: February 2022

### Installation

Installation has to be done in accordance to the Installation Recommendation of **SPORTEC® golf slab EPDM**. The latest version of the Installation Recommendation can be downloaded at the website of KRAIBURG Relastec GmbH & Co. KG.

The product data sheet is not subject to any change service! All information is without guarantee.

Latest version of this document available on [www.kraiburg-relastec.com/sportec](http://www.kraiburg-relastec.com/sportec)

page 3 of 3