





shooting block, cube, step

Product data sheet no. 9144 - R-05

Issue: February 2022

Specifically designed as a projectile-absorbing surfacing material, SPORTEC® shooting blocks provides protection at targets of indoor shooting ranges and nearby outdoor facilities. SPORTEC® shooting blocks reliably absorbs dangerous ricochets and rebounds.

Material

Material:


Recycling tyre rubber granules bonded with polyurethane elastomer.

Product design

Colour(s): red, black, green and grey

(low colour differences are conditional of material)

Colour(s):



red, black, green, grey

Surface: open-pored smooth

Type of floor covering: Safety surface

Latest version of this document available on www.kraiburg-relastec.com/sportec











shooting block, cube, step

Product data sheet no. 9144 - R-05

Issue: February 2022

Dimensions / Tolerances / Weight

Weight: Block:

> approx. 25.5 kg (at 500 mm x 300 mm x 200 mm) approx. 12.75 kg (at 250 mm x 300 mm x 200 mm)

approx. 50.0 kg

Step:

approx. 33.0 kg (at 1000 mm x 300 mm x 150 mm) approx. 29.0 kg (at 1000 mm x 240 mm x 120 mm)

Length x width x height: Block:

> 500 mm / 300 mm / 200 mm (± 0.8 %) 250 mm / 300 mm / 200 mm (± 0.8 %)

Cube:

400 mm / 400 mm / 400 mm (± 0.8 %)

1000 mm / 300 mm / 150 mm (± 0.8 %) 1000 mm / 240 mm / 120 mm (± 0.8 %)

Product Testing

Fire resistance: Efl (B2) (EN 13501-1)

Hardness: 60 ± 5 Shore A (DIN 53505)

-30° C to 80° C (internal tested) Temperature range:

rV = 5.9 (DIN V 18035-6)Wear behaviour:

VOC emission rating:



Latest version of this document available on www.kraiburg-relastec.com/sportec













shooting block, cube, step

Product data sheet no. 9144 - R-05

Issue: February 2022

Installation

Installation has to be done in accordance to the Installation Recommendation of SPORTEC® shooting blocks. The latest version of the Installation Recommendation can be downloaded at the website of KRAIBURG Relastec GmbH & Co. KG.

The product data sheet is not subject to any change service! All information is without guarantee. Latest version of this document available on www.kraiburg-relastec.com/sportec





