

# supercell

**Product data sheet no. 9171 - R - 05**

Issue: January 2025

**SPORTEC® supercell** is a versatile, extremely lightweight foam mat that can be used over its entire surface or as a shock pad for a wide variety of applications. The product is supplied in 2x1 m format and can easily be cut to size.


## Material

Material:

A mixture of recycled PU-foam and Latex granules bonded with polyurethane elastomer

## Product design

Colour(s):



supercell DC2

Surface: granule structure

Note: low colour differences are conditional of material

## Dimensions / Tolerances / Weight

Thickness(es):	10 and 20 mm (-5 / +15%)
Length x width:	2000 mm x 1000 mm (± 10 mm)
Density:	approx. 180 kg/m <sup>3</sup>
Area weight:	1.8 kg/m <sup>2</sup> at 10 mm 3.6 kg/m <sup>2</sup> at 20 mm

The product data sheet is not subject to any change service! All information is without guarantee.

Latest version of this document available on [www.kraiburg-relastec.com/sportec](http://www.kraiburg-relastec.com/sportec)

page 1 of 2

# supercell

Product data sheet no. 9171 - R - 05

Issue: January 2025

## Product Testing

Tensile strength:	min. 0,1 N/mm <sup>2</sup> (EN ISO 1798)
Elongation at break:	min. 55% (EN ISO 1798)
Force reduction:	35% (at 10 mm) (internal tested) 54% (at 20 mm) (internal tested)
Stress -dynamic:	15 mm = 0.019 N/mm <sup>2</sup> (at 10% compression; internal tested) 15 mm = 0.033 N/mm <sup>2</sup> (at 20% compression; internal tested) 15 mm = 0.046 N/mm <sup>2</sup> (at 30% compression; internal tested)  30 mm = 0.029 N/mm <sup>2</sup> (at 10% compression; internal tested) 30 mm = 0.047 N/mm <sup>2</sup> (at 20% compression; internal tested) 30 mm = 0.067 N/mm <sup>2</sup> (at 30% compression; internal tested)

VOC emission rating:



## Installation

Installation has to be done in accordance to the Installation Recommendation of **SPORTEC® supercell** DC 2. The latest version of the Installation Recommendation can be downloaded at the website of KRAIBURG Relastec GmbH & Co. KG.

The product data sheet is not subject to any change service! All information is without guarantee.

Latest version of this document available on [www.kraiburg-relastec.com/sportec](http://www.kraiburg-relastec.com/sportec)

page 2 of 2